

Technical Data

Protective Paint Black High Gloss "Schwarzer Peter"

For indoors and outdoors applications

Technical details PAINT

colour shade	deep black
degree of gloss	high gloss
base of binder	natural asphalt
base of pigment	-
solid content	46,2%
specific weight	0,91 g/cm ³
viscosity at +20 °C	approx. 140s 4 mm, DIN EN ISO 2431
temperature stability	up to +140 °C
flash point	above +21 °C
hazard identification	pls see material safety data sheet
storage	cool and dry
thinning	universal thinner
spray viscosity	-

Advice for handling

application temperature	ideal at approx. +18 - 25 °C
surface preparation	clean, dry, free of grease and rust
primer	-
consistency	ready for use
touch dry at +20 °C	after approx. 60 minutes
fully hardened	after approx. 10-12 hours
recoat	-
coverage	approx. 100 - 120 ml/m ²
cleaning	with universal thinner

Categorisation according to VOC directive: 2004/42 EG	Category "A/i" specialties VOC max. 500 g/l (2010).
This product contains:	<500 g/l VOC

Test results

Cross cut test DIN 53151 / ISO 2409	GT 2
Salt spray test ISO 9227	240 hours
Humidity test DIN 50017	240 hours
T-bend test 5 mm	---
Resistant to oil and petrol (regular)	---
UV-durable	---
Film thickness	approx. 30 µm

Product features

Insulation and protection paint for wood and plaster
Rust and weather resistant
Thermoplastic

Applications

Suitable for decorative parts on stoves, tile ovens, protective grating
and for insulation e.g. eaves and gutters

Store in a dry place and at room temperature (15-25°C), minimum durability two years. Open can with care!

"The Data on this technical information sheet correspond with the current status of our knowledge and experience.
The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights.
We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process".

For more information and samples, please contact:

ECKART GmbH / Günterstal 4 / 91235 Hartenstein / Germany
Tel.: ++ 49-(0) 09152-77-0 / Fax: ++49-(0)-09152-77-4435 / E-mail: info.eckart@altana.com